



VHB™ Adhesive Transfer Tapes with High Performance Acrylic Adhesive 100MP

9460PC • 9469PC • 9473PC • F9460PC • F9469PC • F9473PC • 9469FL

Product Data Sheet

Date: February 2020
Supersedes: July 2018

Product Description

3M™ VHB™ Adhesive Transfer Tapes F9460PC, 9460PC, F9469PC, 9469PC, 9469FL, F9473PC and 9473PC utilize the 3M™ High Performance Acrylic Adhesive 100MP, which has good long term holding power.

Key Features

- For interior and exterior industrial applications to replace rivets, spot welds and other permanent fasteners.
- 3M™ VHB™ Adhesive Transfer Tapes are transparent

Physical Properties

Products	F9460PC 9460PC	F9469PC 9469PC	F9473PC 9473PC
Adhesive thickness*	0,059 mm	0,134 mm	0,272 mm
Liner thickness *	0,100 mm		
Liner weight	100 g/sqm		
Liner material	Polycoated paper, brown		
Liner printing	Versions with "F" prefix have liner printing Versions without "F" have no printing		
Adhesive colour	transparent		

*AFERA 5006

Products	9469FL
Adhesive thickness*	0,125 mm
Liner thickness *	0,100 mm
Liner weight	100 g/sqm
Liner material	Polypropylene, unprinted
Adhesive colour	transparent

Performance Characteristics

Products	F9460PC 9460PC	F9469PC 9469PC 9469FL	F9473PC 9473PC
Adhesion to Stainless Steel (FTM2 - after 72 h RT using 50 µm aluminium foil)	12,0 N/cm	19,5 N/cm	19,5 N/cm
Adhesion to PET (FTM2 - after 72 h RT using 50 µm aluminium foil)	8,7 N/cm	11,1 N/cm	12,4 N/cm
Static Shear (FTM8 - 1000 g/25 mm* 12,5 mm on stainless steel, 150 °C)	> 10,000 Minutes		

Immersion 7 days in Engine oil at 50 °C	No changes in appearance
Immersion 7 days in 5 % salt water	No changes in appearance
7 days high humidity chamber 38 °C, 100 RH	No changes in appearance
7 days automotive cycle 4 h -40 °C, 4 h 90 °C, 16 h 38 °C, 100 % RH	No changes in appearance
Storage 4 h at 260 °C	No changes in appearance
Immersion 1 h in Gasoline	No changes in appearance
Immersion 1 h 5 % H2SO4	No changes in appearance Slight adhesion loss 1 mm at edges
Immersion 1 h 5 % NaOH	No changes in appearance Slight adhesion loss 1 mm at edges

These 3M™ VHB™ Adhesive Transfer Tapes are made from the same adhesive system and are thermoplastic in nature, becoming softer as temperature increases and firmer as temperature decreases. As the adhesive becomes firmer, the adhesion performance generally increases. At low temperatures (lower than -40 °C, the 3M™ VHB™ Adhesive Transfer Tapes become very firm and glassy; the ability to absorb impact energy is reduced.

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength. To obtain optimum adhesion, the bonding surfaces must be clean, dry, and well unified. Some typical surface cleaning solvents are isopropyl alcohol/water mixture or heptane. *

Ideal tape application temperature range is 21 °C to 38 °C. Initial tape application to surfaces at temperatures below 10 °C is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

***Note:** Be sure to follow the manufacturer's precautions and directions for use when using solvents.

Storage & Shelf Life

Store at 16 °C – 25 °C and 40-65 % relative humidity in its original box. The product can be stored up to 18 months after production.

Recognition / Certification

UL-Recognised in File MH17478

Precautionary Information

TSCA: These products are defined as articles under the Toxic Substances Certification Control Act and therefore, are exempt from inventory listing requirements.

MSDS: These products are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, the products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.

For Additional Information

To request additional product information or to arrange for sales assistance, call.....
Address correspondence to: 3M

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark the 3M Company.



3M United Kingdom plc
3M Industrial Adhesive and Tapes Division
3M Centre
Cain Road Bracknell
Berkshire RG12 8HT
Tel: 0870 60 800 50

3M Ireland Limited
3M Industrial Adhesive and Tapes Division
The Iveagh Building
The Park
Carrickmines, Dublin 18
Tel: Tel: 1 800 320 500